

Polymer **CR/SBR**
Code **R140**

1. DIMENSIONS AND APPEARANCE

Bun size (W x L x T)	in	Contact for availability
Colour		Black

2. PROPERTIES

Density	pcf	8 - 15	ASTM D1056
	kg/m ³	128 - 240	ASTM D1056
Compression deflection (25%)	psi	2 - 5	ASTM D1056
	kPa	14 - 34	ASTM D1056
Hardness	Shore OO	25 - 45	ASTM D2240
Compression set (50%)	%	35 max.	ASTM D1056
Tensile strength	psi	80 min.	ASTM D412
	kPa	552 min.	ASTM D412
Elongation	%	300 min.	ASTM D412
Water absorption	%w	10 max.	ASTM D1056
Fluid immersion (Fuel B)	%	250 max.	ASTM D1056
Low working temp	°F	-40	
High working temp	°F	200	
Flammability		PASS	FMVSS 302

3. SPECIFICATIONS

ASTM D1056-67	SCE41
ASTM D1056-14	2C1