

Polymer **CR Based**  
Code **R451-B**

---

## 1. DIMENSIONS AND APPEARANCE

---

Bun size (W x L x T)	in	40 x 48 x 1.25
Colour		Black

---

## 2. PROPERTIES

---

Density	pcf	15 - 23	ASTM D1056
	kg/m <sup>3</sup>	240 - 368	ASTM D1056
Compression deflection (25%)	psi	17 - 24	ASTM D1056
	kPa	117 - 165	ASTM D1056
Hardness	Shore OO	60 - 80	ASTM D2240
Compression set (50%)	%	25 max.	ASTM D1056
Tensile strength	psi	150 min.	ASTM D412
	kPa	1034 min.	ASTM D412
Elongation	%	175 min.	ASTM D412
Water absorption	%w	5 max.	ASTM D1056
Fluid immersion (7 days, 73.4°F)	%	150 max.	ASTM D1056 Fuel B
Low working temp	°F	-40	
High working temp	°F	200	
Flammability		PASS	FMVSS 302

---

## 3. SPECIFICATIONS

---

ASTM D1056-67	SCE45
ASTM D1056-14	2C5